



Product information

Product full identity:

Unplasticised Polyvinyl Chloride

U-PVC is rated self-extinguishing, has excellent chemical resistance with high mechanical and tensile strength, together with a high degree of stability. U-PVC is easily weldable but has a limited operating temperature range of 0°C to +60°C.

Properties

- » Machines well to a polished finish
- » Solvent Cemented & Welded
- » Relatively less expensive than other plastics
- » Strong and stiff
- » Flame retardant grades available
- » Chemical resistant
- » Self extinguishing
- » UV stabalised grades available
- » Drinking water approved
- » Food compliant grades available

Applications

- » Corrosive fluid handling
- » Valves
- » Tanks
- » Water applications
- » Air conditioning & ventilation systems

This document contains

- » Technical Datasheet (Page 2)
- » Chemical Datasheet (Page 3)
- » Safety Datasheet (Pages 4-5)

For any furthur information regarding food, fire and water certificates then please contact the sales team on 01767 310 327



Technical Properties

| Physical Properties | Test | Unit | Result |
|---|-------------|-----------------|------------------------|
| 1. Specific gravity | ISO 1183 | g/cm³ | 1.37 |
| Maximum service temp. Upper temp limit (no stronger mechanical stress involved) | - | °C | 60 |
| 3. Lower temp limit | - | °C | 0 |
| Mechanical Properties | Test | Unit | Result |
| 1. Elongation at yield | ISO 527 | % | 4 |
| 2. Yield Stress | ISO 527 | MPa | 73 |
| 3. Impact strength | ISO 179 | kJ/m² | - |
| 4. Notch impact strength | ISO 179 | kJ/m² | 3 |
| 5. Ball indentation | ISO 2039-1 | MPa | - |
| 6. Shore-D | ISO 868 | - | 84 |
| 7. Modulus of elasticity | ISO 527 | MPa | 3300 |
| Thermal Properties | Test Method | Unit | Result |
| 1. Coefficient of linear thermal expansion | DIN 53752 | k ⁻¹ | 0.8 x 10 ⁻⁴ |
| 2. Thermal conductivity | DIN 52612 | W/(m*K) | 0.159 |
| Electrical Properties | Test Method | Unit | Result |
| 1. Surface resistivity | IEC 6093 | Ω | >1014 |
| 2. Dielectric strength | IEC 60243-1 | kV/mm | 30 |
| Additional Data | Test Method | Unit | Result |
| 1. Bondability | - | - | - |
| 2. Food compliance | FDA + EU | - | - |
| 3. Flammability | UL 94 | - | V-0 > 1mm |
| | | | |

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Кеу:

| Yes | Limited | No data |
|-----|---------|---------|
| + | 0 | - |



Chemical Properties

| Agent | Conc % | Working | Temp | Agent | Conc % | Working | Temp |
|---------------------------|---------|---------|------|----------------------------|-------------|---------|------|
| | | 20°C | 60°C | Hydrofloric acid | 40 | + | 0 |
| Acetic Acid | 100 | + | - | Hydrogen peroxide | 10 | + | + |
| Acetone | 100 | - | - | Hydrogen Sulphide | | + | + |
| Ammonia | Conc. | + | 0 | Isopropyl Alcohol | 100 | + | + |
| Ammonium chloride | | + | + | Mercurochrome | | 0 | - |
| Amyl Alcohol | | + | 0 | Methyl alcohol | 100 | + | +/o |
| Benzene | | - | - | Methyl ethyl ketone | 100 | - | - |
| Bleaching Solution | 12,5 CI | + | - | Methylene chloride | 100 | - | - |
| Boric Acid | 100 | + | 0 | Nitric acid | 50 | + | + |
| Brake Fluid | | + | + | Nitrobenzine | | - | + |
| Butyl Acetate | | - | - | Oxalic Acid | | + | + |
| Calcium Chloride | | + | + | Ozone, gas | ca. 0,5 ppm | + | + |
| Carbon disulphide | 100 | - | - | Paraffin Oil | 100 | + | 0 |
| Carbon Tetrachloride | | - | - | Perchlorethylene | | - | - |
| Chlorine, gas | 100 | 0 | - | Petroleum | 100 | + | + |
| Chlorobenzene | 100 | - | - | Petroleum, aromatic free | 100 | + | + |
| Chloroform | | - | - | Phenol, aqu | ca.9 | 0 | - |
| Citric Acid | 10 | + | _ | Phosphoric Acid | 50 | + | + |
| Cresol | | - | - | Potassium hydroxide liquor | 50 | + | + |
| Cyclohexanone | 100 | - | - | Propyl alcohol | | + | О |
| Cyclohexene | 100 | + | 0 | Pyridine | | - | - |
| Diesel Fuel | | + | О | Silicone oil | | + | + |
| Diethylene oxide, THF | | - | - | Sodium carbonate. aqu | | + | + |
| Ethyl acetate | 100 | - | - | Sodium chloride, aqu | | + | + |
| Ethyl alcohol | 96 | + | 0 | Sodium Hydroxide liquor | 15 | 0 | 0 |
| Ethylene Chloride | 100 | - | - | Sodium Hydroxide liquor | 60 | 0 | О |
| Formic Acid | 10 | + | 0 | Sodium hydrogen sulphite | | + | + |
| Frost protection agent | Petrol | + | + | Sodium nitrate, aqu | | + | + |
| Fuel, aromatic free | | + | + | Sodium thiosulfate | | + | + |
| Glycerine | 100 | + | + | Sulphuric Acid | 96 | + | +/0 |
| Glycol | 100 | + | + | Tetrahydrofurance | 100 | - | - |
| Heating oil | | + | + | Toluene | 100 | - | - |
| Heptane | 100 | + | + | Trichlorethylene | 100 | - | - |
| Hydrochloric acid | conc. | + | + | Xylene | | - | - |

All The above information is for guide purposes only. The data has been taken from standard test results provided by our manufacturers.

Кеу:

| Yes | Limited | No data |
|-----|---------|---------|
| + | 0 | - |





Safety Properties

Substance / preparation and company detail

Polyvinylchloride Anglia Plastics Unit 13 Albone Way Biggleswade Bedfordshire SG18 8BN

Composition / indications to components

Chemical characteristics: polymer of vinyl chloride

CAS-number: not necessary

Possible dangers

Unknown

First-aid measures

General comment: medical aid is not necessary

First-aid measures: none Routes of exposure: none Symptoms / effects: none

First-fighting measures

In case of fire please use gas mask and breathing equipment in depending of circulating air. Fire residues must be disposed of according to the local instructions. Suitable fire-fighting appliance: water fog, foam, fire fighting powder, carbon dioxide

Hazard warning notice: not applicable

Measures in case of unintended release

Person-related measures: none

Environmental protection measures: not applicable

Cleaning equipment: not applicable

Unsuitable cleaning products: not applicable

Handing and storage

Handling: no special regulations must be observed Storage: unlimited good storage property

Limitation of exposition

Special design of techn. processing facilities: not required

Tolerance levels: none

Exposure measurement procedures: none Respiratory protection: not required

Eye protection: not required Body protection: not required





Safety Properties

Physical and chemical characteristics

Phenotype

Phenotype / form: semi-finished product, solid state

Colour: transparent Smell: not applicable Change of state

Flash point: not applicable

Other remarks
Density: 1.44 g/cm3

Stability and reactivity

Thermal decomposition: above appr. 200°C

Dangerous decomposition products:

Besides hydrochloric acid also carbon dioxide and water will develop during the burning process. In case of incomplete

burning also carbon monoxide and traces of phosgene may arise.

Use of stabilisers: none Exothermic reactions: none

Notices regarding state of aggregation: none

Conditions to be avoided: none Substances/media to be avoided: none

Toxic information

During several years of usage no effects being harmful for the health were observed.

Ecological information

No biodegradation, no solubility in water, no effects being harmful to the environment must be expected.

Mobility: not applicable Accumulation: not applicable Eco-toxicity: not applicable

Waste-disposal information

Can be recycled or can be disposed of together with household rubbish (acc. To local regulations).

Waste key for the unused product: EAK-Code 120 105

Waste name: waste of polyvinylchloride

Transport information

No dangerous product in respect to / according to transport regulations Notice/symbol transport containers: none

Special marking for containers: none

Regulations

Marking according to GefStoffV/EG: no obligation for marking

Water danger class: class 0 (self classification) Domestic requirements to be observed: none

Further information

The information is based on our current knowledge. They are meant to describe our products in respect to safety requirements. They do not represent any guarantee of the described product in the sense of the legal guarantee regulations.